

ชื่อวิทยานิพนธ์	การวัดค่าคงที่พีโซอิเล็กทริกโดยอาศัยเทคนิคทางอินเทอร์เฟอโรมิเตอร์
ผู้เขียน	นายปัญญา แชน้ำแก้ว
สาขาวิชา	ฟิสิกส์
ปีการศึกษา	2545

บทคัดย่อ

เทคนิคอินเทอร์เฟอโรมิเตอร์เป็นเทคนิคที่ใช้ในการวัดการกระจัดหรือแอมพลิจูดของการสั่น เนื่องจากได้รับสนามไฟฟ้ากระแสสลับในสารพีโซอิเล็กทริกได้ถึงระดับเศษส่วนของอังสตรอม อินเทอร์เฟอโรมิเตอร์แบบไมเคิลสันเป็นระบบที่มีเลเซอร์ ซีเลียม-นियोอน เป็นแหล่งกำเนิดแสงความถี่เดียวและมีการแบ่งลำแสงออกเป็น 2 ลำแสงด้วยตัวแบ่งแสง ลำแสงหนึ่งตกกระทบกระจกอ้างอิง อีกลำแสงหนึ่งจะตกกระทบกับสารตัวอย่างที่ต้องการรู้ค่าคงที่พีโซอิเล็กทริก ลำแสงทั้งสองจะสะท้อนกลับมาที่ตัวแบ่งแสงและแทรกสอดกัน โดยที่ความเข้มแสงที่รีวแทรกสอดขึ้นกับผลต่างทางเดินของสองลำแสง มีการใช้หัววัดแสงและเครื่องขยายสัญญาณล็กอิน ช่วยในการอ่านค่าความเข้มแสงในรูปของศักย์ไฟฟ้าซึ่งมีความสัมพันธ์กับการกระจัด อัตราส่วนของการกระจัดต่อศักย์ไฟฟ้าที่ขับเคลื่อนสารตัวอย่างคือค่าคงที่พีโซอิเล็กทริก งานวิจัยนี้ได้ปรับเทียบระบบอินเทอร์เฟอโรมิเตอร์ โดยอาศัยผลึกเดี่ยวลิเทียมนิโอเบต จากนั้นวัดค่าคงที่พีโซอิเล็กทริกในแนวความหนาของ พีโซเซรามิก เลดเซอร์โคเนตไทเทเนต ได้เท่ากับ (270 ± 50) พิโคเมตรต่อโวลต์ ทำให้ได้ว่าค่าลึงแยกการกระจัดของระบบอินเทอร์เฟอโรมิเตอร์อยู่ในระดับ 10^{-12} เมตร จากการค้นคว้าเพิ่มเติม พบว่าการศึกษาคงที่ของพีโซอิเล็กทริกในสารกึ่งตัวนำมีไม่มากนัก สาเหตุจากการมีสภาพนำไฟฟ้าสูง และค่าคงที่พีโซอิเล็กทริกมีค่าน้อย ระบบอินเทอร์เฟอโรมิเตอร์ที่มีค่าลึงแยก 10^{-12} เมตร ไม่สามารถตรวจวัดการกระจัดของสารกึ่งตัวนำได้ งานวิจัยนี้จึงปรับปรุงเสถียรภาพของอินเทอร์เฟอโรมิเตอร์เพื่อประยุกต์ใช้กับสารกึ่งตัวนำเกลเลียมอาร์เซไนด์ จากการทดลองให้สนามไฟฟ้าที่มีความถี่ในช่วง 4 - 20 กิโลเฮิร์ตซ์ ได้ค่าคงที่ พีโซอิเล็กทริกของเกลเลียมอาร์เซไนด์เท่ากับ (2.8 ± 0.1) พิโคเมตรต่อโวลต์ ซึ่งสอดคล้องกับค่าที่รายงาน ผลการทดลองที่ได้บ่งชี้ความละเอียดของการวัดการกระจัดของระบบฯ ว่าอยู่ในระดับ 10^{-13} เมตร มีการตรวจสอบการตอบสนองพีโซอิเล็กทริกของสารกึ่งตัวนำที่ประกอบด้วยฟิล์มบางเกลเลียมอาร์เซไนด์และอลูมิเนียมเกลเลียมอาร์เซไนด์ พบว่า สารตัวอย่างมีการสั่นเมื่อความถี่มีค่า 10 กิโลเฮิร์ตซ์ ขึ้นไปจากกราฟความสัมพันธ์ระหว่างและศักย์ไฟฟ้า พบว่า การกระจัดมีแนวโน้มเพิ่มขึ้นแบบฟังก์ชันเชิงเส้นกับศักย์ไฟฟ้าความชันกราฟมีค่าประมาณ 1.3 พิโคเมตรต่อโวลต์ ซึ่งก็คือขนาดของค่าคงที่พีโซ อิเล็กทริก สนามพีโซอิเล็กทริกที่เกิดขึ้นในสารคาดว่าถูกเหนี่ยวนำให้เกิดขึ้นจากความเครียดบริเวณรอยต่อของฟิล์มบาง

Thesis Title Piezoelectric Coefficient Measurement Using Interferometric Techniques
Author Mr. Panya Kheanumkaw
Major Program Physics
Academic Year 2002

Abstract

An interferometric technique was used to measure a displacement or a vibrational amplitude in a sub-angstrom range caused by an external applied electric field for a piezoelectric material. A Michelson interferometer used a He-Ne laser as a monochromatic light source. The laser beam was split into two beams by a beam splitter. The first beam incident on a reference mirror and the second one on a sample whose the piezoelectric coefficient was unknown. The beams reflected back from the sample and the mirror recombined at the beam splitter and formed an interference pattern. The intensity at the interference pattern depends on an optical path length difference of the two beams. An optical detector and a lock-in amplifier were used to convert an optical signal into a voltage, which related to the sample displacements. A ratio between the displacement and the driving voltage is a piezoelectric coefficient. This work calibrated the optical system using a single crystal of lithium niobate. Afterwards, the extensional of lead zirconate titanate ceramics was measured and piezoelectric coefficient was found to be (270 ± 50) pm/V . A displacement resolution of the system was consequently determined to be of the order of 10^{-12} meter. From further literature survey, the piezoelectric responses in semiconductors were rarely reported due to their high electrical conductivity and small values of the piezoelectric coefficient. The 10^{-12} -meter resolution was not capable of measuring the the displacement of the semiconducting materials. The present work improved the stabilization of the interferometer and applied to the measurements of semiconducting gallium arsenide. From the measurement in a frequency range of 4 – 20 kHz , the piezoelectric coefficient of GaAs was found to be (2.8 ± 0.1) pm/V , which agreed well with a reported value. This result indicated that the displacement resolution of the system was of the order of 10^{-13} meter. Investigations of the piezoelectric response were carried out for semiconductor of the thin films of gallium arsenide and aluminum gallium arsenide. The sample vibrations were observed at the frequencies of 10 kHz and

above. From the graph of the displacement-voltage relation, the measured displacements tended to be linear with the voltages. A slope of the graph was approximately 1.3 pm/V , hence, a magnitude of the piezoelectric coefficient. The piezoelectric field in this material was anticipated that it was induced by the strain at the interfaces of the thin films.