

ชื่อวิทยานิพนธ์	การวัดทางไพเอโซอิเล็กทริกและไพโรอิเล็กทริกสำหรับคอมโพสิต BaTiO ₃ /PVDF
ผู้เขียน	นายสุไลมาน หะยีสะอะ
สาขาวิชา	ฟิสิกส์
ปีการศึกษา	2549

บทคัดย่อ

ในงานวิจัยนี้ได้ขยายช่วงคุณสมบัติของวัสดุให้กว้างขึ้น โดยการเตรียมคอมโพสิต BaTiO₃/PVDF ใช้แบเรียมไททาเนต (BaTiO₃) สัดส่วนโดยปริมาตรของเซรามิกต่ำ (ϕ) คือ 0.15 และ 0.30 ใส่ในพอลิเมอร์เมตริกพอลิไวนิลิดีนฟลูออไรด์ (PVDF) ที่ถูกละลายด้วยสารละลาย เอ็นเมธิลพิพโรลิโดน (NMP) ในอัตราส่วน 10 : 90 เปรอร์เซ็นต์โดยน้ำหนัก (wt%) ตามลำดับ กวนของผสมอย่างต่อเนื่องที่อุณหภูมิ 60 °C เป็นเวลา 6 ชั่วโมง ขึ้นรูปคอมโพสิตเป็นแผ่นด้วยวิธีการแบบเทป และนำไปอบอ่อนที่อุณหภูมิ 120 °C เป็นเวลา 6 ชั่วโมง ทำให้ได้คอมโพสิตที่มีความหนาอยู่ในช่วง (28 ± 3) μm เมื่อตรวจสอบจุลโครงสร้างด้วยกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกวาด (SEM) พบว่าคอมโพสิตที่เตรียมขึ้นมีการเรียงติดกันแบบ 0-3 เป็นส่วนใหญ่ อีกแบบหนึ่งคือ แบบ 3-3 จากนั้นนำคอมโพสิตผ่านกระบวนการโครโนโพลิงที่อุณหภูมิห้อง 25 °C เมื่อตรวจสอบค่าความจุความร้อนของคอมโพสิต 0.15 ϕ และ 0.30 ϕ พบว่าเท่ากับ 3021.7 J/kg °C และ 865.7 J/kg °C ตามลำดับ ไม่สังเกตเห็นการตอบสนองทางไพเอโซอิเล็กทริกของคอมโพสิต 0.15 ϕ สำหรับคอมโพสิต 0.30 ϕ ที่ผ่านการโพลิงสองเฟสในทิศเดียวกันและในทิศตรงข้ามกัน ค่าคงที่ไพเอโซอิเล็กทริกเท่ากับ (8.7 ± 0.1) pm/V และ (11.3 ± 0.1) pm/V ตามลำดับ สำหรับคอมโพสิต 0.15 ϕ ที่ไม่โพลิง โพลิงทั้งสองเฟสในทิศเดียวกันและในทิศตรงข้ามกันมีค่าคงที่ไดอิเล็กทริกที่ 1 kHz เท่ากับ 0.80, 9.75 และ 8.77 ตามลำดับและค่าการสูญเสียไดอิเล็กทริกเท่ากับ 0.43, 0.20 และ 0.30 ตามลำดับ ในขณะที่คอมโพสิต 0.30 ϕ ที่มีเงื่อนไขโพลิง 3 แบบเช่นเดียวกันกับ 0.15 ϕ มีค่าคงที่ไดอิเล็กทริกเท่ากับ 0.80, 11.48 และ 9.77 ตามลำดับและค่าการสูญเสียไดอิเล็กทริกเท่ากับ 0.48, 0.21 และ 0.31 ตามลำดับ ค่าคงที่ไพโรอิเล็กทริกสำหรับคอมโพสิต 0.15 ϕ ที่โพลิงทั้งสองเฟสในทิศเดียวกันและในทิศตรงข้ามกัน เท่ากับ 25 $\mu\text{C}/\text{m}^2\text{°C}$ และ 19 $\mu\text{C}/\text{m}^2\text{°C}$ ตามลำดับ ในขณะที่คอมโพสิต 0.30 ϕ ที่มีเงื่อนไขโพลิงทำนองเดียวกัน เท่ากับ 41 $\mu\text{C}/\text{m}^2\text{°C}$ และ 24 $\mu\text{C}/\text{m}^2\text{°C}$ ตามลำดับ จากการศึกษาชี้ให้เห็นว่าคอมโพสิตที่น่าสนใจสำหรับประยุกต์ใช้ทางอิเล็กทรอนิกส์ที่ต้องการสิ่งประดิษฐ์น้ำหนักเบา ไม่เป็นพิษต่อสิ่งแวดล้อม ผลิตง่ายและราคาข่อมเยว่

Thesis Title	Measurements of Piezoelectricity and Pyroelectricity for BaTiO ₃ /PVDF Composites
Author	Mr. Sulaiman Hajeesaeh
Major Program	Physics
Academic Year	2006

ABSTRACT

This work extended the range of material properties by fabricating the BaTiO₃/PVDF composite, a low volume fraction (ϕ) of 0.15 and 0.30 of barium titanate (BaTiO₃) were filled in a matrix of polyvinylidene fluoride (PVDF) which was dissolved by 1-methyl-2-pyrrolidone (NMP) with a ratio of 10:90 wt%, respectively. The mixture was stirred at the temperature of 60 °C for 6 hours. The composite was shaped by a tape casting method before annealing at 120 °C for 6 hours and the thickness of the composite, which was flexible, was $(28 \pm 3) \mu\text{m}$. The microstructure of the composite was observed using scanning electron microscopy (SEM) and found that the connectivity of the composite was mainly 0-3 and the other one was 3-3. Subsequently, the composite was undergone a corona poling at room temperature of 25 °C. Heat capacity for the composite of 0.15 ϕ and 0.30 ϕ were 3021.7 J/kg °C and 865.7 J/kg °C, respectively. The piezoelectric response was not observed in the 0.15 ϕ composite. For the composite with both phase poled parallelly, the 0.30 ϕ one had the piezoelectric constant of $(8.7 \pm 0.1) \text{ pm/V}$ and $(11.3 \pm 0.1) \text{ pm/V}$, respectively. The 0.15 ϕ composites which were unpoled, poled parallelly and antiparallelly had the dielectric constant (1 kHz) of 0.80, 9.75 and 8.77, respectively and the dielectric loss of 0.43, 0.20 and 0.30, respectively. For the 0.30 ϕ composites under 3 poling conditions as the 0.15 ϕ had the dielectric constant of 0.80, 11.48 and 9.77, respectively, and the dielectric loss of 0.48, 0.21 and 0.31, respectively. The pyroelectric constants for the 0.15 ϕ composite with both phase poled parallelly and antiparallelly were $25 \mu\text{C/m}^2\text{°C}$ and $19 \mu\text{C/m}^2\text{°C}$, respectively. For the 0.30 ϕ composite with the same poling conditions the values were $41 \mu\text{C/m}^2\text{°C}$ and $24 \mu\text{C/m}^2\text{°C}$, respectively. This study implied that the

composites are attractive for electronic applications where a light, environmentally friendly, ease to fabricate and low-cost device is required.