

ชื่อวิทยานิพนธ์	สภาวะที่เหมาะสมต่อการผลิตถ่านกัมมันต์จากขี้เลือยไม้ยางพารา
ผู้เขียน	นางสาวศิษณุภรณ์ เครือสุวรรณ์
สาขาวิชา	วิศวกรรมเคมี
ปีการศึกษา	2549

บทคัดย่อ

ขี้เลือยไม้ยางพาราเป็นวัสดุเหลือใช้จำนวนมากจากอุตสาหกรรมเฟอร์นิเจอร์ไม้ยางพาราในภาคใต้ ขี้เลือยกุกน้ำมามเพิ่มน้ำมูลค่าโดยสามารถนำมาผลิตเป็นตัวคูดซับในอุตสาหกรรมได้ หากทำการเปลี่ยนสภาพโครงสร้างพื้นผิวดองขี้เลือยอย่างเหมาะสม ในงานวิจัยนี้เป็นการหาสภาวะที่เหมาะสมต่อการผลิตถ่านกัมมันต์จากขี้เลือยไม้ยางพาราโดยใช้สารละลายน้ำฟอสฟอริกและไอ้น้ำเป็นตัวกระตุน การกระตุนทางเคมีทำโดยแซ่ดด้วยกรดฟอสฟอริก แล้วจึงทำการคาร์บอนไซเดน เช่น ออกไซด์ และการคาร์บอนไซเดนในเช่นเดียวกัน ตามความต้องการของสารเคมีในช่วง 1:1–1:2 ออกไซด์ในกระบวนการกระตุนในช่วง 400-700 องศาเซลเซียส และระยะเวลาในการกระตุนในช่วง 45-90 นาที และควบคุมชั้นตอนการกระตุนต่อไปที่คงที่ทุกสภาวะ สำหรับการกระตุนด้วยไอ้น้ำ ขอบเขตการทดลองหาสภาวะที่เหมาะสมในงานวิจัยนี้มีดังนี้ อัตราส่วนขี้เลือยต่อสารเคมีในช่วง 1:1–1:2 ออกไซด์ในการกระตุนในช่วง 400-700 องศาเซลเซียส และระยะเวลาในการกระตุนในช่วง 45-90 นาที และควบคุมชั้นตอนการกระตุนต่อไปที่คงที่ทุกสภาวะ สำหรับการกระตุนด้วยไอ้น้ำ ในช่วง 30-60 นาที ออกไซด์ในกระบวนการกระตุนในช่วง 500-800 องศาเซลเซียส และระยะเวลาในการกระตุนในช่วง 45-90 นาที นอกจากนี้เทคนิค Response Surface Method (RSM) ถูกนำมาใช้เพื่อหาสภาวะที่เหมาะสมโดยใช้ตัวแปรหลักประกอบด้วย ร้อยละผลได้ (yield) พื้นที่ผิว BET และการคูดซับไอโอดีน โดยสภาวะที่เหมาะสมสำหรับการกระตุนด้วยกรดฟอสฟอริกซึ่งคืออัตราส่วนขี้เลือยต่อสารเคมีเป็น 1:1.5 ออกไซด์ 550 องศาเซลเซียส เวลา 68 นาที ให้ค่าพื้นที่ผิวเท่ากับ $1331.82 \text{ m}^2/\text{g}$ ค่าการคูดซับไอโอดีน 580.32 mg/g ร้อยละผลได้เท่ากับ 52.29 และสภาวะที่เหมาะสมสำหรับการกระตุนด้วยไอ้น้ำ คือ เวลาในการกระตุน 45 นาที ออกไซด์ 650 องศาเซลเซียส เวลาในการกระตุน 68 นาที สามารถผลิตถ่านกัมมันต์ได้พื้นที่ผิว $978.03 \text{ m}^2/\text{g}$ ค่าการคูดซับไอโอดีน 645.73 mg/g ร้อยละผลได้เท่ากับ 44.88

Thesis Title	Optimum Conditions of Activated Carbon Production from Rubber Wood Sawdust
Author	Miss Sitsadaporn Kruasawan
Major Program	Chemical Engineering
Academic Year	2006

ABSTRACT

Rubber wood sawdust as an industrial furniture waste was enhanced by produce to activated carbon. In this work, rubber wood sawdust was sieved to a selected particular size and determined moisture content and its component by methods of proximate analysis and ultimate analysis. A two-stage activation procedure (carbonization, followed by activation at a desired high temperature) was used for the production of activated sample using chemical activation by phosphoric acid (H_3PO_4) and steam activation. The experiments of H_3PO_4 activation were carried out to investigate the influences of impregnation ratio between rubber wood sawdust : acid in range of 1:1-1:2, activation temperature in range 400-700 °C and activation time in range 45-90 min. Another part of this research was focused in the activated carbon produced by steam activation using different carbonization time 30-60 min, activation temperature 500-800°C and activation time 45-90 min. The experiments were conducted in a stainless steel tube heated by a cylindrical electric furnace under nitrogen. The properties of activated carbons were evaluated on these followings: Brauner Emmet Teller (BET) surface area, Iodine number, pH, yield, moisture content and density. Moreover, the technique of Response Surface Method (RSM) was also applied to obtain the experimental design to determine the optimum conditions of activated carbon production from rubber wood sawdust by steam and H_3PO_4 activation. The H_3PO_4 activation at 550 °C for 68 min with impregnation ratio 1:1.5 are achieved maximum BET surface area $1331.82\text{ m}^2/\text{g}$ with iodine adsorption 580.32 mg/g and product yield of 52.29%. The optimum conditions of steam activation are carbonization time 45 min and activation temperature 650 °C for 68 min are achieved maximum BET surface area $978.03\text{ m}^2/\text{g}$ with iodine adsorption 645.73 mg/g and product yield of 44.88%