

## บทคัดย่อ

รหัสโครงการ : MRG 4680024

ชื่อโครงการ : การสังเคราะห์วัสดุเซรามิกผสม อะลูมินา-ซิลิกอนคาร์บีนเดอร์ จากดินขาว

ชื่อนักวิจัย : ผศ. ดร. สุธรรม นิยมวารส

ภาควิชาชีวกรรมเครื่องกล คณะวิศวกรรมศาสตร์ มหาวิทยาลัยสงขลานครินทร์

Sutham.n@psu.ac.th

ชื่อนักวิจัยที่ปรึกษา : รศ. ดร. เล็ก ศีกคง

ระยะเวลาโครงการ : 1 กรกฎาคม 2546 ถึงวันที่ 31 ตุลาคม 2549

งานวิจัยนี้มีจุดประสงค์เพื่อสังเคราะห์วัสดุเซรามิกผสม  $\text{Al}_2\text{O}_3$ -SiC จากดินขาว (แหล่งจังหวัดระนอง) โดยวิธีปฏิกรณ์การบีบตัวซึ่ง และศึกษาตัวแปรที่มีผลกระทบต่อการสังเคราะห์ คือ เวลาในกระบวนการตั้งต้น (1-48 ชั่วโมง) อุณหภูมิการสังเคราะห์ ( $1400 - 1600^\circ\text{C}$ ) อัตราส่วนเริงโมลของสารตั้งต้นcarbon:nอนต่อดินขาว (6-10) เวลาในการอบสังเคราะห์ (30 - 60 นาที) และอัตราการไหลของแก๊สออกซิเจน (1-5 LPM) เพื่อวิเคราะห์และเสนอแนวทางที่ดีที่สุดในการสังเคราะห์  $\text{Al}_2\text{O}_3$ -SiC จากดินขาว

การทดลองเริ่มจากการตั้งต้นดินขาวและถ่านกัมมันต์ตามสัดส่วน บดผสมสารตั้งต้นนำอนุภาคผสมไปวางในเตาอบที่บริเวณกึ่งกลางเตา ภายหลังจากปิดหน้าแปลนฝาท่อของเตาอบเรียบร้อยแล้ว จึงเปิดชุดควบคุมการไหลของแก๊สออกซิเจนให้แก๊สออกซิเจนไหลปกคลุมระบบภายในเตาอบ หลังจากนั้นปรับชุดควบคุมอุณหภูมิให้เริ่ม การทำความร้อนภายในเตาอบ โดยมีรั้นตอนการทำความร้อนคือ จากอุณหภูมิห้องสูง  $1500^\circ\text{C}$  เพิ่มขึ้นด้วยอัตรา  $10^\circ\text{C min}^{-1}$  และจาก  $1500^\circ\text{C}$  สูง  $1600^\circ\text{C}$  เพิ่มขึ้นด้วยอัตรา  $5^\circ\text{C min}^{-1}$  และให้รักษาอุณหภูมิไว้ที่  $1600^\circ\text{C}$  หรืออุณหภูมิที่จะศึกษาตามเวลาที่ต้องการ หลังจากนั้นชุดควบคุมอุณหภูมิก็จะตัดการทำงาน เพื่อให้เตาอบเย็นตัวลงจนเข้าสู่อุณหภูมิห้อง อนุภาคผสมที่ได้จากการสังเคราะห์ถูกนำไปวิเคราะห์ด้วยวิธี XRD และ SEM เพื่อศึกษาขนาดของสารประกอบ และลักษณะโครงสร้างพื้นผิวของอนุภาคผสม

จากการทดลองศึกษาผลกระทบของตัวแปรต่างๆ พบร่วมปฏิกรณ์เกิดสมบูรณ์ และสามารถสังเคราะห์วัสดุผสม  $\text{Al}_2\text{O}_3$ -SiC จากดินขาว เมื่อบดสารตั้งต้นด้วยอัตราส่วนเริงโมลของcarbon:nอนต่อดินขาว เท่ากับ 6 นาน 6 ชั่วโมง นำไปสังเคราะห์ที่  $1600^\circ\text{C}$  เป็นเวลา 1 ชั่วโมง ภายใต้บาริยากรของแก๊สออกซิเจนที่อัตราการไหล 1 LPM

คำนลักษก : วัสดุเซรามิกผสม  $\text{Al}_2\text{O}_3$ -SiC ปฏิกรณ์การบีบตัวซึ่ง รีดตัวซึ่ง ดินขาว

## Abstract

Project Code: MRG 4680024

Project Title: Synthesis of  $\text{Al}_2\text{O}_3$ -SiC Ceramic Composite Materials from Kaolin

Investigator: Asst. Prof. Dr. Sutham Niyomwas

E-mailAddress: sutham.n@psu.ac.th

Project Period: July 1, 2003 to October 31, 2006

The objective of this research project is to synthesize  $\text{Al}_2\text{O}_3$ -SiC composites by carbothermal reduction of kaolin (Ranong based). The research intends to study the effects of process parameters to the synthesized products. The studied process parameters are the reactants milling time (1-48 hr.), synthesized temperature ( $1400 - 1600^\circ\text{C}$ ), carbon to kaolin mole ratio (6-10), soaking time at synthesized temperature (30 – 60 min.) and argon gas flow rate (1-5 LPM). The results were characterized and the best condition to synthesize  $\text{Al}_2\text{O}_3$ -SiC from kaolin was presented.

Kaolin and activated carbon were weighted as of studied molar ratio and milled in planetary ball-milled. This mixed powder was loaded into alumina crucible and placed it in the middle of the tube furnace. The furnace was heated in a programmed manner from room temperature to  $1500^\circ\text{C}$  at  $10^\circ\text{C min}^{-1}$  and  $1500^\circ\text{C}$  to  $1600^\circ\text{C}$  at  $5^\circ\text{C min}^{-1}$ . Soaking at the final temperature for 1 hr or as of studied, then the furnace was turned off, allowing the products cool in the furnace. The product powders were characterized using XRD (PHILIPS with Cu K $\alpha$  radiation) and SEM (JEOL, JSM-5800 LV) analyses.

From the experimental results we found that the complete reaction to synthesis  $\text{Al}_2\text{O}_3$ -SiC composites from kaolin can be achieved via process conditions as carbon to kaolin mole ratio of 6, milling time of 6 hr., synthesized temperature of  $1600^\circ\text{C}$  at soaking time of 60 min. and argon gas flow rate of 1 LPM.

**Keywords :**  $\text{Al}_2\text{O}_3$ -SiC ceramic composite, carbothermal reduction reaction, kaolin