

การเตรียมความติดไม้จากยางธรรมชาตินามาเลอท

บทคัดย่อ

เตรียมยางธรรมชาตินามาเลอทหรือยางธรรมชาตigriff์มาเลอิกแอน ไช่ไดร์ค จากปูกิริยาโคพอลิเมอร์เชิงของยางธรรมชาติกับนามาเลอิกแอน ไช่ไดร์ค 4, 6 และ 8 phr เมนโซ้อลิเดปอร์ออกไซด์ 3 phr ในโกลุอินที่อุณหภูมิ 80 °C เป็นเวลา 1, 1.5, 2, 2.5 และ 3 ชั่วโมง ภายใต้บรรบากาศในโตรเจน วิเคราะห์หาปริมาณการกรีฟ์ของนามาเลอิกแอน ไช่ไดร์คด้วยอินฟราเรดสเปกโถโรโนโนเมทรี โดยใช้อัตราส่วนพื้นที่ไดพีค $A_{1854} + A_{1776} + A_{1716}/A_{836}$ เปรียบเทียบกับกราฟมาตรฐานที่ไดจากการทดสอบยางธรรมชาติกับนามาเลอิกแอน ไช่ไดร์คทางกายภาพในคลอโรฟอร์ม จากการทดลองพบว่าเบอร์เซ็นต์การกรีฟ์เพิ่มขึ้นเมื่อปริมาณนามาเลอิกแอน ไช่ไดร์คและเวลาในการทำปูกิริยาเพิ่มขึ้น เตรียมสูตรกวารติดไม้โดยการทดสอบยางธรรมชาตินามาเลอทที่มีปริมาณการกรีฟ์ 1.46, 2.54, 3.56 หรือ 4.41 % กับโกลุอิน โพಡสเซียน ไอเดอท ไคฟินลามีน และ wood rosin ปริมาณต่างๆ จากการทดลองพบว่าไดสูตรกวารที่เหมาะสมที่มีค่า shear strength และ cleavage peel strength สูงสุดเท่ากับ 98.48 lb/in^2 และ 2.44 kN/m เมื่อใช้ยางธรรมชาตินามาเลอท (กรีฟ์ 2.54 %), 5 % โพଡสเซียน ไอเดอท, 1 % ไคฟินลามีน, และ 20 % wood rosin ค่า shear strength และ cleavage peel strength เพิ่มขึ้นตามอัตราการเก็บที่นานขึ้น การทุกสูตรทบทวนต่อหน้าได้นานกว่า 30 วัน

Preparation of Wood Adhesive from Maleated Natural Rubber

Abstract

The maleated natural rubber (MNR) or natural rubber grafted maleic anhydride (NR-g-MAH) was prepared from copolymerization of natural rubber with maleic anhydride 4, 6 and 8 phr, benzoyl peroxide 3 phr in toluene at 80 °C for 1, 1.5, 2, 2.5 and 3 hrs in nitrogen atmosphere. The grafting percentage of maleic anhydride was determined by FTIR spectrophotometry using peak area ratio of $A_{1854}+A_{1776}+A_{1716}/A_{836}$ compared to the standard curve of NR/maleic anhydride physical mixture in chloroform. It was found that the percentage of grafting increased with the increasing of maleic anhydride and reaction time. The wood adhesives were formulated from blending of 1.46, 2.54, 3.56 or 4.41 %grafting of MNR with toluene, potassium oleate, diphenylamine and different amounts of wood rosin. The optimum adhesive formulation with maximum shear strength and cleavage peel strength of 98.48 lb/in² and 2.44 kN/m was found from using MNR (2.54 % grafting), 5 % potassium oleate, 1 % diphenylamine and 20 % wood rosin. The shear strength and cleavage peel strength increasing of storage duration and all adhesive formulations were resistant in water more than 30 days.