

ชื่อวิทยานิพนธ์	ลักษณะเฉพาะของวัสดุไพโอโซอิเล็กทริกสำหรับการประยุกต์ใช้เป็น ทรานสดิวเซอร์ทางคลื่นเสียง
ผู้เขียน	นายสมศักดิ์ คงสกุล
สาขาวิชา	ฟิสิกส์
ปีการศึกษา	2549

บทคัดย่อ

งานวิจัยนี้เตรียมสารไพโอโซเซรามิกที่ไม่มีตะกั่วเป็นองค์ประกอบอันได้แก่ KNbO_3 และ BaTiO_3 ให้มีความพรุน 10-30% โดยวิธีปฏิกิริยาตรงใช้อุณหภูมิแคลไซน์ 900 °C และขึ้นรูปสารเป็นเม็ด โดยการให้แรงอัดและความร้อนในเวลาเดียวกัน ก่อนนำไปเผาซินเตอร์ที่ 1000°C จากการทดสอบสารความพรุนต่างๆ พบว่า BaTiO_3 ความพรุนประมาณ 23 % ความหนา 0.3-0.5 mm มีค่าที่น่าสนใจทางอุทกสถิตินั้นคือ ϵ_r เท่ากับ 3036 ค่า k_p เท่ากับ 0.368 ค่า k_t เท่ากับ 0.241 ค่า z เท่ากับ 3.746 นอกจากนั้น g_h เท่ากับ $2.56 \text{ mVm}^{-1}\text{Pa}^{-1}$ d_h เท่ากับ 0.029 pCN^{-1} ค่า FoM เท่ากับ $2.493 \times 10^{-15} \text{ Pa}^{-1}$ ค่า M เท่ากับ $32.95 \text{ } \mu\text{VPa}^{-1}$ ค่า B เท่ากับ 4.214 GPa สารตัวอย่างนี้เหมาะสมสำหรับใช้เป็นตัวส่งคลื่นอะคูสติกในน้ำ ส่วน KNbO_3 ที่มีความพรุน 28% และมีความหนา 0.1-0.3 mm ที่มีค่า ϵ_r เท่ากับ 1453 ค่า k_p เท่ากับ 0.207 ค่า k_t เท่ากับ 0.182 ค่า z เท่ากับ 4.590 ค่า g_h เท่ากับ $3.26 \text{ mVm}^{-1}\text{Pa}^{-1}$ ค่า d_h เท่ากับ 0.050 pCN^{-1} ค่า FoM เท่ากับ $3.617 \times 10^{-15} \text{ Pa}^{-1}$ ค่า M เท่ากับ $54.870 \text{ } \mu\text{VPa}^{-1}$ ค่า B เท่ากับ 7.529 GPa สารตัวอย่างนี้เหมาะสมสำหรับใช้เป็นตัวรับคลื่น

Thesis Title Characterization of Piezoelectric Materials for Applications as an Acoustic Transducer

Author Mr. Somsak Kongsakoon

Major Program Physics

Academic Year 2006

ABSTRACT

This project prepared lead-free piezoceramic ,e.g.,KNbO₃ and BaTiO₃ with 10 – 30 % porosity using the direct method. Calcined temperature used was 900 °C and a disk shape was formed by an application of pressure and heat and sintered the samples at 1000 °C. From the measurements of all samples with different porosities, the 23 % porosity BaTiO₃ is of interesting for hydrostatic work, i.e., ϵ_r of 3036, k_p of 0.368, k_t of 0.241 , z of 3.746. In addition, g_h , d_h , FoM, M and B are 2.56 mVm⁻¹Pa⁻¹, 0.029 pCN⁻¹, 2.493 x10⁻¹⁵ Pa⁻¹, 32.95 μVPa⁻¹ and 4.214 GPa , respectively. This sample is suitable for transmitting acoustic wave in water. For 28% porosity KNbO₃ , 0.1- 0.3 mm thick, those values are ϵ_r of 1453, k_p of 0.207, k_t of 0.182 , z of 4.590 . In addition, g_h , d_h , FoM, M and B are 3.26 mVm⁻¹Pa⁻¹, 0.050 pCN⁻¹, 3.617 x10⁻¹⁵ Pa⁻¹, 54.870 μVPa⁻¹ and 7.529 GPa , respectively. This sample is promising for receiving acoustic wave.