

ชื่อวิทยานิพนธ์	การทำรูปพรุนขนาดเล็กมากบนแผ่นเยื่อบางพอลิเมอร์ด้วยเทคนิคทางนิวเคลียร์
ผู้เขียน	นายวิฑูร สุจริตธุระการ
สาขาวิชา	ฟิสิกส์
ปีการศึกษา	2547

บทคัดย่อ

ในการศึกษาการทำรูปพรุนขนาดเล็กมากบนแผ่นพอลิเมอร์ด้วยเทคนิคทางนิวเคลียร์ ณ ห้องปฏิบัติการฟิสิกส์นิวเคลียร์ ภาควิชาฟิสิกส์ มหาวิทยาลัยสงขลานครินทร์ แผ่นฟิล์มบางที่มีขายในเชิงพาณิชย์ทำมาจากวัสดุเซลลูโลสไนเตรต CN85 และแผ่นโพลีคาร์บอนเนตที่มีความหนา $6\ \mu\text{m}$ และ $670\ \mu\text{m}$ ได้ถูกนำมาใช้ในการศึกษาครั้งนี้ ด้วยการระดมยิงด้วยอนุภาคแอลฟาที่ถูกปลดปล่อยออกมาจากสารกัมมันตรังสี Am^{241} แบบจุดที่มีขนาดความแรงกัมมันตภาพรังสี $0.877\ \mu\text{Ci}$ เป็นเวลานาน 5, 10 และ 20 นาที ตามลำดับ ในขณะที่แผ่นโพลีคาร์บอนเนตที่มีความหนา $6\ \mu\text{m}$ และ $670\ \mu\text{m}$ จะถูกระดมยิงด้วยอนุภาคแอลฟาจากปฏิกิริยานิวเคลียร์ $^{10}\text{B}(n, \alpha)^7\text{Li}$ ซึ่งนิวตรอนในปฏิกิริยานิวเคลียร์ดังกล่าวเกิดขึ้นจากแหล่งกำเนิดนิวตรอน $^{238}\text{Pu}-^9\text{Be}$ ของภาควิชาฟิสิกส์ มหาวิทยาลัยสงขลานครินทร์ ขนาดความแรงกัมมันตภาพรังสี $16.9\ \text{Ci}$ เป็นเวลานาน 30, 60 และ 120 นาที ตามลำดับเช่นเดียวกัน ในการขยายขนาดของรูปพรุนที่แผ่อยู่บนแผ่นฟิล์มจะอาศัยสารเคมี $6.25\ \text{N NaOH}$ ที่มีอุณหภูมิสูง 85°C เป็นเวลา 5-25 นาที ในการศึกษารูปร่างขนาดเส้นผ่าศูนย์กลาง รวมทั้งความหนาแน่นของรูปพรุนต่อหน่วยพื้นที่จะอาศัยกล้องจุลทรรศน์ รวมทั้งกล้องจุลทรรศน์อิเล็กตรอนด้วย สำหรับการศึกษาลักษณะของเมมเบรนที่เกิดจากกระบวนการผลิตดังกล่าว จะศึกษาด้วยอัตราการกรองน้ำ ซึ่งพบว่าถ้าใช้แรงอัดสูงขึ้น อัตราการไหลของน้ำจะลดลง ซึ่งสาเหตุน่าจะเกิดจากมีรูปพรุนที่เป็นรูปรกวยแต่เฉียงเกิดขึ้นเป็นจำนวนมาก ซึ่งน่าจะเกิดจากการที่อนุภาคแอลฟาที่พุ่งชนแผ่นฟิล์มที่ไม่ได้ตั้งฉากกับแผ่นฟิล์มเป็นจำนวนมาก

Thesis Micropore Piercing on Polymer Membrane Using Nuclear
Track-Etch Technique
Author Mr.Witoon Sutjaritturakan
Major Program Physics
Academic Year 2004

Abstract

Micro pore piercing on polymer film by nuclear track-etched technique were studied at Nuclear Physics Laboratory, Physics department, Prince of Songkla University. The commercially available cellulose nitrate CN85 thin film and polycarbonate films with the thickness of 6 μm and 670 μm were bombarding with an alpha particles from an Am -241 point source with the activity of 0.877 μCi for 5, 10 and 20 minutes, respectively. While polycarbonate films with the thickness of 6 μm and 670 μm film was exposed with alpha particles from $^{10}\text{B}(n, \alpha)^7\text{Li}$ nuclear reaction. The previous nuclear reaction employed the thermal neutron particles from $^{238}\text{Pu}-^9\text{Be}$ neutron source that belong to the Physics department, PSU with an activity of 16.9 Curies to bombard the CN85B film for 30, 60 and 120 minutes, respectively also. All the bombarding films were etched in 6.25 N NaOH at 85 $^{\circ}\text{C}$ for 5-25 minutes etching time. Both SEM and optical microscopes were used to observe the pore shape, diameter and also the pore density per unit area were investigated. In order to characterize the nuclear track-etch produced membrane, the flow rate of water filtration was also performed. It was noted that at higher pressures the hydraulic conductivity declined with pressure, probably because the track-etched pores, as evidenced by atomic force microscopy were not normal to the membrane surface and this may have caused a partial collapse of the pores at higher pressures etched pores were not normal to the membrane surface.